

- 2. ASPHALT JOINTS SHALL BE SAND SEALED WITH CRS-1 OR CRS-2 EMULSIFIED ASPHALT OR EQUIVALENT.
- 3. CONTROL DENSITY FILL SHALL BE USED ON COLLECTOR AND ARTERIAL STREETS. REFER TO CITY DETAIL 210.



CITY OF HAPPY VALLEY ENGINEERING DIVISION 16000 SE MISTY DRIVE HAPPY VALLEY, OR 97086 **DWG NO: 205**

<u>CITY ENGINEER</u> CAROL EARLE, P.E. TRENCH RESTORATION WITH GRANULAR BACKFILL

DATE: 4/1/2019

REVISED BY: PCB/JHH